

GEOLOGY
Limestone

BEST USE
Exterior Walls of Buildings and Fireplace Stone Shall be Mortared In

WEIGHT CALCULATOR PER SQUARE FOOT OF FLATS AND LINEAL FOOT OF CORNERS
14.9 Lbs Average Per Sf
19.1 Lbs Average Per Lf

QUANTITY PER PALLET/CRATE
Full Bed Veneer: 4000 Lbs (80-85 SF)
Thin Veneer: 150SF (2,200-2,300 Lbs)
200SF (3,000-3,100)



TOSCANO Traditional

FULL VENEER

Common Coverage
Standard joint **Dry Stack** **Overgrout**
40 square feet / ton 30 Sf / ton 50 Sf / ton

DIMENSIONS
2" high X 8"-18" lengths
4" high X 8"-18" lengths
6" high X 8"-18" lengths
8" high X 8"-18" lengths
10" high X 8"-18" lengths
12" high X 8"-18" lengths
Thickness: 3"-5"

TYPICAL PIECE
Sawn Top and Bottom w/ Snapped Ends
Rectilinear Shape

STANDARD SIZE TOLERANCE
Height: 1/8" +/- Less
Thickness: 3"-5.5"

SHIPPING DETAILS: FULL TRUCK QUANTITY
Flatbed: 12-13 Pallets
Dry Van: 12-13 Pallets
Rail Container: 12-13 Pallets

THIN VENEER

Common Coverage per crate
Standard joint **Dry Stack** **Overgrout**
200 square feet 180 Sf / ton 220 Sf / ton

DIMENSIONS
2" high X 8"-18" lengths
4" high X 8"-18" lengths
6" high X 8"-18" lengths
8" high X 8"-18" lengths
10" high X 8"-18" lengths
12" high X 8"-18" lengths
Thickness: 1"-1.5"
Corner Returns: 3"-5"

TYPICAL PIECE
Sawn Top and Bottom w/ Snapped Ends
Rectilinear Shape

STANDARD SIZE TOLERANCE
Height: 1/8" +/- Less
Thickness: 1"-1.5"

SHIPPING DETAILS: FULL TRUCK QUANTITY
Flatbed: 21-22 Pallets / 17-18 Crates
Dryvan: 19-20 Pallets / 15-16 Crates
Rail Container: 18-19 Pallets / 14-15 Crates

ASTM TESTING

Average Dry Weight (g).....	564.7
Average Saturated Weight (g).....	613.8
Average Suspended Weight (g).....	328.9
Average 48-hr Absorption (%).....	9.21
Average Bulk Specific Gravity	1.98
Average Modulus of Rupture (DRY) (psi)	439.9
Average Modulus of Rupture (WET) (psi).....	606.9
Average Compressive Strength (DRY) - Perpendicular (psi).....	2,103.6
Average Compressive Strength (DRY) - Parallel (psi)	2,586.0
Average Compressive Strength (WET) - Perpendicular (psi).....	2,208.8
Average Compressive Strength (WET) - Parallel (psi)	2,122.4