

GEOLOGY

Limestone

BEST USE

Exterior Walls of Buildings and Fireplace Stone Shall be Mortared In

WEIGHT CALCULATOR PER CUBIC FOOT OF MATERIAL

$$\frac{12 \times 12 \times \text{Thickness}}{1728} = ft^3$$
$$ft^3 \times 145 \text{ lbs} = \text{Weight (lbs) per SF}$$

QUANTITY PER PALLET/CRATE

Varies per dimensions requested, speak with your sales representative for more information



NADIA NEO PLANKS

DIMENSIONS

- 2" high X 12"-30" lengths
- 4" high X 12"-36" lengths
- 6" high X 12"-36" lengths
- 8" high X 12"-48" lengths
- 10" high X 12" – 48" lengths
- 12" high X 12"-48" lengths
- 16" high X 24"-48" lengths
- 18" high X 24"-48" lengths
- 24" high X 24"-48" lengths
- Standard Thickness: .75", 1", 1.25", 1.5", 2.25", 3", 4"
- Corners: 2"-24" high X up to 18" lengths w/ 4" returns
- Available Finishes: Honed, Brushed, Bush Hammered, Pin Striped

TYPICAL PIECE

- Sawn 6 sides w/ Finished Face
- Rectilinear Shape

STANDARD SIZE TOLERANCE

- Width / Length: 1/16" +/- Less
- Thickness: 1/8" +/- Less
- Square: 1/16" +/- Less

SHIPPING DETAILS: FULL TRUCK QUANTITY

Calculated per dimensions requested, speak with you sales representative for more information

ASTM TESTING

Density (lbs/CuFt)	145.5
Absorption (%)	4.8
Specific Gravity	2.38
Modulus of Rupture (psi)	1,361
Compressive Strength (psi)	9,870