

## GEOLOGY

Limestone

## BEST USE

Exterior Walls of Buildings and Fireplaces Stone Shall be Mortared In

## WEIGHT CALCULATOR PER SQUARE FOOT OF FLATS AND LINEAL FOOT OF CORNERS

14.9 Lbs Average Per Sf

19.1 Lbs Average Per Lf

## QUANTITY PER PALLET/CRATE

Full Bed Veneer: 4,000 Lbs

Thin Veneer: 150 Sf (2,200-2,300 Lbs)  
200 (3,000-3,100)



**CAMILLA Recs**

## FULL VENEER

|                       |                  |                  |
|-----------------------|------------------|------------------|
| Common Coverage       |                  |                  |
| <b>Standard Joint</b> | <b>Dry Stack</b> | <b>Overgrout</b> |
| 40 Square Feet / Ton  | 30 Sf / Ton      | 50 Sf / Ton      |

### DIMENSIONS

|               |        |
|---------------|--------|
| Random Sizes: | 3"-10" |
| Thickness:    | 3"-5"  |

### TYPICAL CHARACTERISTICS

Chopped All Sides  
Random Rectangular Shapes

### STANDARD SIZE TOLERANCE

|            |         |
|------------|---------|
| Thickness: | 3"-5.5" |
|------------|---------|

### SHIPPING DETAILS: FULL TRUCK QUANTITY

|                 |               |
|-----------------|---------------|
| Flatbed:        | 12-13 Pallets |
| Dry Van:        | 12-13 Pallets |
| Rail Container: | 12-13 Pallets |

## THIN VENEER

|                       |                  |                  |
|-----------------------|------------------|------------------|
| Common Coverage       | Per Crate        |                  |
| <b>Standard Joint</b> | <b>Dry Stack</b> | <b>Overgrout</b> |
| 200 Square Feet       | 180 Sf / Ton     | 220 Sf / Ton     |

### DIMENSIONS

|                 |         |
|-----------------|---------|
| Random Sizes:   | 3"-10"  |
| Thickness:      | 1"-1.5" |
| Corner Returns: | 3"-5"   |

### TYPICAL PIECE

Chopped All Sides  
Random Rectangular Shapes

### STANDARD SIZE TOLERANCE

|            |         |
|------------|---------|
| Thickness: | 1"-1.5" |
|------------|---------|

### SHIPPING DETAILS: FULL TRUCK QUANTITY

|                 |                              |
|-----------------|------------------------------|
| Flatbed:        | 21-22 Pallets / 17-18 Crates |
| Dry Van:        | 19-20 Pallets / 15-16 Crates |
| Rail Container: | 18-19 Pallets / 14-15 Crates |

### ASTM TESTING

|                                   |        |
|-----------------------------------|--------|
| Compressive Strength (psi) .....  | 12,520 |
| Flexural Strength (g).....        | 2,330  |
| Freeze/Thaw Loss (%) .....        | 0.00   |
| Average 48-hr Absorption (%)..... | 1.8    |